



RUST-OLEUM® AUTOMOTIVE HIGH PERFORMANCE WHEEL

DESCRIPTION AND USES

Rust-Oleum® High Performance Wheel enhances the look and color of automobile wheels and helps prevent the formation of rust. It is suitable for use on plastic hubcaps and wheels made of aluminum or steel. High Performance Wheel features an advanced spray system that allows you to spray at any angle, even upside down for those hard to reach areas. A comfort spray tip with a wider finger pad reduces fatigue caused by continuous spraying.

PRODUCTS

SKU	DESCRIPTION (11 oz. spray)
248927	Steel
248928	Matte Black
248929	Clear
248930	Graphite

PRODUCT APPLICATION

READ ALL INSTRUCTIONS CAREFULLY BEFORE STARTING PROJECT

SURFACE PREPARATION

Wash the surface with a commercial detergent, or other suitable cleaning method. Rinse with fresh water and dry with a clean cloth. Thoroughly wipe down the wheel surface with Rust-Oleum Wax & Tar Remover. Remove loose paint and rust with a wire brush or sandpaper. Lightly sand smooth and glossy surfaces. For best results, use Rust-Oleum Adhesion Promoter or sand surface with #1000 grit sandpaper.

WARNING: If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead

PRODUCT APPLICATION (cont.)

APPLICATION

Use outdoors or in a well ventilated area such as an open garage. Use when temperature is between 50-90°F (10-32°C) and humidity is below 85% to ensure proper drying. Do not apply to surfaces, when heated, exceed 200°F (93°C) or galvanized metal. Avoid spraying in very windy and dusty conditions. Cover surrounding area to protect from spray mist.

Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle DO NOT STRIKE CAN. Contact Rust-Oleum. Shake often during use. Hold can upright 10-16" from surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can in motion while spraying. For best appearance, apply one light coat followed by one wet coat. Do not use near open flame.

DRY & RECOAT


Dry and recoat times are based on 70°F and 50% relative humidity. Allow more time at cooler temperatures. Dries to touch in 10 minutes and is fully dry in 30 minutes. To improve the finish gloss, apply a topcoat of High performance Wheel Clear after 10 minutes.

CLEAN-UP

Wipe off tip when finished. Clean-up wet paint with xylene or mineral spirits. Properly discard empty container. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

	TECHNICAL DATA	ATO-40
RUST-OLEUM® AUTOMOTIVE HIGH PERFORMANCE WHEEL		

PHYSICAL PROPERTIES

		HIGH PERFORMANCE WHEEL
Resin Type		Acrylic
Pigment Type		Proprietary
Solvents		Acetone, Toluene, Xylene
MIR		1.25 Max
Fill Weight		11 ounces
Recommended Dry Film Thickness (DFT) Per Coat		1.0-2.0 mils (25-50μ)
Practical Coverage at Recommended DFT		8-10 sq. ft./can (0.74-0.93 m ² /can)
Dry Times @ 70-80°F (21-27°C) and 50% Relative Humidity	Touch	10 minutes
	Recoat	10 minutes
	Fully Dry	30 minutes
Shelf Life		5 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see SDS

Calculated values are shown and may vary slightly from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.