



Fusion All-in-One™

Hammered Finish

2782, 2783, 2785, 2786, 2787, 2788

PRODUCT DESCRIPTION	APPLICATION	CAUTIONS
FUSION ALL-IN-ONE™ provides maximum rust protection, ultimate strength, bonds to tough surfaces and offers a no sand, no prime application. Use on all metals, wood, plastic, laminates, masonry, concrete, wicker, ceramic, glass, plaster and hard-to-adhere surfaces.	Shake can 1 to 2 minutes and during use. Test spray in an inconspicuous area for compatibility. Hold can 8" to 10" from surface. Spray in sweeping motion side-to-side, with slight overlap. Surfaces can be sprayed at any angle. Apply multiple thin coats. Wait 1 minute between each coat. Dries to touch in 20 minutes. Handle in 1 hour. Apply additional coats within 2 hours or after 48 hours. To clean paint on actuator, wear eye protection and wipe off with lacquer thinner, following solvent manufacturer's instruction. DO NOT stick pin in dial opening. Recycle empty can and cap per local regulations.	CONTAINS ACETONE, LT ALIPHATIC HYDROCARBON SOLVENT, PROPANE, ETHYBENZENE, BUTANE, XYLENE. DANGER! EXTREMELY FLAMMABLE. Keep away from heat, sparks, and open flame. Vapors will accumulate readily and may ignite explosively. Keep area ventilated during use and until all vapors are gone. DO NOT SMOKE - Extinguish all flames, pilot lights and heaters - Turn off stoves, electric tools and appliances, and any other sources of ignition. CONTENTS UNDER PRESSURE. Avoid prolonged exposure to sunlight or heat from radiators, stoves, hot water and other heat sources that may cause bursting. Do not puncture, incinerate, burn or store above 120°F. Keep upright in a cool, dry place. Do not discard empty can in trash compactor. VAPOR HARMFUL. Use with adequate ventilation. Avoid continuous breathing of vapor and spray mist. To avoid breathing vapors or spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air or wear respiratory protection (NIOSH approved) or leave the area. Avoid contact with eyes and skin. Wash hands after using. FIRST AID: In case of eye contact, flush thoroughly with large amounts of water for 15 minutes and get medical attention. For skin contact, wash thoroughly with soap and water. In case of respiratory difficulty, provide fresh air and call physician. DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE. Contains solvents which can cause permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents can be harmful or fatal. WARNING: This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm. DANGER: Rags, steel wool, other waste soaked with this product, and sanding residue may spontaneously catch fire if improperly discarded. Immediately place rags, steel wool, other waste soaked with this product, and sanding residue in a sealed, water-filled, metal container. Dispose of in accordance with local fire regulations. DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN. CONFORMS TO ASTM D-4236. Contact a physician for more health information.
PAINTING CONDITIONS	Color: Various Coverage: Estimated 25 square feet Drying Time, @ 77 °F, 50% RH: Drying time and recoat times are temperature, humidity, and film thickness dependent To Touch: 20 minutes To Handle: 1 hour Re coat: Within 2 hours or after 48 hours	
SURFACE PREPARATION	Vehicle Type: Alkyd Finish: Hammered Volume Solids: 11-13% Weight Solids: 17-24%	
WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. Contact the National Lead Information Hotline at 1-800-424-LEAD or log onto www.epa.gov/lead . Surface should be clean, dull & dry. Remove loose rust and paint with wire brush or sand paper.		PERFORMANCE TESTING
		Technical data furnished herein is accurate and true to the best of our knowledge. However, no guarantee of accuracy is expressed or implied. We assume no responsibility or liability as a result of purchase, coverage, application or injuries resulting in misuse. To contact us call 1-800-247-3268 or ask@krylon.com .