


## **U1P-Drive Full Synthetic Motor Oil**

# **5W-30 API SP, ILSAC GF-6A**

Auto - Light Truck | United States

#### **Product Description**

U1P-DRIVE SAE 5W-30 Full Synthetic Motor Oil, API SP, ILSAC GF-6A is a high performance full synthetic multigrade motor oil formulated for gasoline engines, combining 100% full synthetic base stocks with an Ultra-premium high performance additive package. This oil is designed for use in carbureted, fuel injected, turbocharged, and supercharged gasoline engines in both normal and extreme operating conditions.



#### **Features and Benefits**

- Longer Engine life.
- Excellent overall lubrication and wear protection even at extreme driving conditions.
- Provides excellent cold start lubrication and reduces friction for better gas millage and control of emissions.
- Prevents the formation of varnishes, sludge and deposits that could be generated at high temperatures.
- Maximum protection against corrosion and rust formation.
- Reduces lubricant evaporation at high temperatures.
- Outstanding stable performance within the maximum oil change interval recommended by the vehicle's manufacturer.










#### **Product Code**

Presentation	SKU	Manufacture ID	UPC
1.05 QT / 1 Liter	UFS0530SPGF6AL	UL103	810050650243
1 US Gallon	UFS0530SPGF6AG	UL103	810050650236
1 JUG (5 QTS)	UFS0530SPGF6AJ	UL103	810050658287
5 Gallon Pail	UFS0530SPGF6AP	UL103	810050650229
55 Gallon Drum	UFS0530SPGF6AD	UL103	810050650212
265 Gallon Tote	UFS0530SPGF6AT	UL103	810050650205



# This product meets or exceeds the requirements of: API SP, API SN, API SM, API SL and API SJ Chrysler MS6395 Fiat 9.55535-CR1 Kia





### **Properties and Specifications\***

Parameter	Result
Appearance	Amber, liquid
Viscosity @ 40°C, cSt, ASTM D445	61.25
Viscosity @ 100°C, cSt, ASTM D445	10.8
Viscosity index, ASTM D2270	170
CCS Apparent Viscosity, cP, ASTM D5293	5,200@-35°C
MRV Apparent Viscosity, cP, ASTM D4684	18,000@-40°C
Pour point, °C, ASTM D97	-42
Flash point, °C, ASTM D92	215
	The second secon



<sup>\*</sup>Typical Properties are typical of those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are to be expected during normal manufacture and at different blending locations. The information contained herein is subject to change without notice.

Revised: 03/06/2023